

= 81 08926-2
Cited as PCT

✓

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C09D 201/02		A1	(11) International Publication Number: WO 97/44402
			(43) International Publication Date: 27 November 1997 (27.11.97)
(21) International Application Number: PCT/US97/08179		(81) Designated States: AU, BR, CA, CN, IL, JP, KR, MX, NZ, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 14 May 1997 (14.05.97)			
(30) Priority Data: 08/650,079 17 May 1996 (17.05.96) US		Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).			
(72) Inventors; and (75) Inventors/Applicants (for US only): BARSOTTI, Robert, John [US/US]; 4167 Coles Mill Road, Franklinville, NJ 08322 (US). HAZAN, Isidor [US/US]; 14 Cnadlestick Road, Clementon, NJ 08021 (US). NEFF, Bruce, Lyle [US/US]; 2325 Kennwynn Road, Wilmington, DE 19810 (US).			
(74) Agent: COSTELLO, James, A.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).			
(54) Title: MAR-RESISTANT OLIGOMERIC-BASED COATINGS			
(57) Abstract <p>A curable coating composition comprising functionalized oligomer components i and ii which cross-link at cure to form a three-dimensional network having chains of substantially uniform, controllable molecular weight between cross-links; oligomers i and ii having weight average molecular weights not exceeding about 3,000, a polydispersity for (i) not exceeding about 1.5, and functionalities that react with one another to cross-link i and ii at cure to yield coatings with an excellent balance of hardness and mar resistance.</p>			

BEST AVAILABLE COPY

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TC	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE**MAR-RESISTANT OLIGOMERIC-BASED COATINGS****BACKGROUND OF THE INVENTION**

5 The present invention relates to a curable coating composition particularly useful as a topcoat in multi-layered coating systems.

 Basecoat-clearcoat systems have found wide acceptance in the past decade as automotive finishes. Continuing effort has been directed to such coating systems to improve the overall appearance, the clarity of the topcoat, and the
 10 resistance to deterioration. Further effort has been directed to the development of coating compositions having low volatile organic content (VOC). A continuing need exists for coating formulations which provide outstanding performance characteristics after application, and particularly mar-resistance and resistance to environmental etching. Heretofore, mar-resistant coatings were attained by
 15 softening the coating, which depreciates other performance characteristics. The instant invention overcomes this problem.

SUMMARY OF THE INVENTION

 This invention concerns a curable coating composition of a binder in
 20 an organic solvent, the composition having a volatile organic content not exceeding about 0.4 kilograms per liter, comprising:

- i) a binder selected from a linear or branched cycloaliphatic moiety-containing oligomer or blend of oligomers with a weight average molecular weight not exceeding about 3,000, a polydispersity not
 25 exceeding about 1.5 and functionality A or A plus B; and
 - ii) an optional oligomeric crosslinker or blend of crosslinkers with a weight average molecular weight not exceeding about 3,000 and functionality C or C plus D;
- components i and ii reacting at cure to form a three-dimensional network having
 30 chains of substantially uniform, controllable molecular weight between crosslinks.

 Preferred functionalities in oligomeric components i and ii are as follows:

<u>COMPONENT (i)</u>	<u>COMPONENT (ii)</u>
A = hydroxyl	C = isocyanate
35 A = hydroxyl	C = melamine
A = anhydride	C = epoxy
A = anhydride	C = epoxy; D = hydroxyl
A = acid	C = epoxy
A = acid; B = hydroxyl	C = epoxy; D = melamine

	A = epoxy	C = isocyanate
	A = epoxy; B = hydroxyl	C = isocyanate
	A = aldimine	C = isocyanate
	A = aldimine; B = hydroxyl	C = isocyanate
5	A = ketimine	C = isocyanate
	A = ketimine; B = hydroxyl	C = isocyanate
	A = silane	C = silane
	A = silane; B = hydroxyl	C = melamine
	A = silane; B = hydroxyl	C = isocyanate
10	A = silane; B = epoxy	C = acid; D = melamine

The compositions of this invention, comprising (i) when (i) is self-crosslinking, or, (i) plus (ii), may also contain up to a total of about 30% based on the total binder of a noncyclic oligomer and/or an acrylic polymer and/or a dispersed
 15 macromolecular polymer as described in more detail hereafter. This invention also concerns a method for coating a substrate comprising applying the disclosed composition thereto and curing the composition; as well as a substrate coated with the composition. The term "isocyanate(s)" employed herein includes blocked isocyanate(s) as well.

20

DETAILS OF THE INVENTION

The compositions of this invention form structured polymer networks of high hardness and excellent mar resistance. The functionality of these oligomers is predictably (nonrandomly) located versus polymers in which functionality is
 25 randomly distributed and whose polydispersities generally exceed 2.0. By "polydispersity" is meant weight average molecular weight divided by number average molecular weight, both measured by gel permeation chromatography. In compositions of this invention, molecular weight between crosslinks can be controlled to form more uniform networks minimizing short, embrittling lengths and
 30 long, softening lengths; minimizing soluble non-functional materials in the network and maximizing the toughness of the films (energy to break). These systems develop open networks with high molecular weight between crosslinks, vs. polymeric systems, at relatively high Tg's.

The Tg of these systems can be controlled to give a maximum
 35 balance of mar, hardness, durability, and etch. In measuring Tg of crosslinked films made from compositions of this invention using dynamic mechanical analysis, the Tg regime is characterized by a steep slope versus a gradual slope for a random system based on polymers. The reactivity of these systems is such that complete reaction is attainable to minimize hydrophilic groups. These systems are typically baked at

120° to 141°C (250° to 285°F), but can be cured at lower temperatures through the use of more reactive groups and catalysis.

Representative of the functionalized oligomers that can be employed as component i or ii are the following:

5 Acid Oligomers: The reaction product of multifunctional alcohols such as pentaerythritol, hexanediol, trimethylol propane, and the like, with cyclic monomeric anhydrides such as hexahydrophthalic anhydride, methylhexahydrophthalic anhydride, and the like.

10 Hydroxyl Oligomers: The above acid oligomers further reacted with monofunctional epoxies such as butylene oxide, propylene oxide, and the like.

Anhydride Oligomers: The above acid oligomers further reacted with ketene.

Silane Oligomers: The above hydroxyl oligomers further reacted with isocyanato propyl trimethoxy silane.

15 Epoxy Oligomers: The diglycidyl ester of cyclohexane dicarboxylic acid, such as Araldite® CY - 184 from Ciba Geigy, and cycloaliphatic epoxies, such as ERL® - 4221, and the like from Union Carbide.

20 Isocyanate Oligomers: The isocyanurate trimer of hexamethylene diisocyanate, DESMODUR® 3300 from Bayer or Tolonate HDT® from Rhone-Poulenc, and the isocyanurate trimer of isophorone diisocyanate, and the like.

Aldimine Oligomers: The reaction product of isobutyraldehyde with diamines such as isophorone diamine, and the like.

Ketimine Oligomers: The reaction product of methyl isobutyl ketone with diamines such as isophorone diamine.

25 Melamine Oligomers: Commercially available melamines such as CYMEL® 1168 from Cytec Industries, and the like.

30 AB-Functionalized Oligomers: Acid/hydroxyl functional oligomers made by further reacting the above acid oligomers with 50%, based on equivalents, of monofunctional epoxy such as butylene oxide or blends of the hydroxyl and acid oligomers mentioned above or any other blend depicted above.

CD-Functionalized Crosslinkers: Epoxy/hydroxyl functional crosslinkers such as the polyglycidyl ether of Sorbitol DCE - 358® from Dixie Chemical or blends of the hydroxyl oligomers and epoxy crosslinkers mentioned above or any other blend as depicted above.

35 The compositions of this invention may additionally contain up to 30% by weight of binder of a noncyclic oligomer, i.e., one that is linear or aromatic. Such noncyclic oligomers can include, for instance, succinic anhydride- or phthalic anhydride-derived moieties in the "Acid Oligomers" such as described above.

Preferred oligomers (i) have weight average molecular weight not exceeding about 3,000 with a polydispersity not exceeding about 1.5; more preferred oligomers have molecular weight not exceeding about 2,500 and polydispersity not exceeding about 1.4; most preferred oligomers have molecular weight not exceeding about 2,200, and polydispersity not exceeding about 1.25. The compositions of this invention can comprise 100% by weight of component (i) when (i) is a self-crosslinker. More typically, compositions will comprise 20-80 weight percent of (i), preferably 30 to 70 weight percent and more preferably 40 to 60 weight percent, with the balance being (ii).

The present coating composition can further comprise a functional amount of catalyst, generally about 0.1 to 5 weight percent, based on the weight of solids in the formulation. A wide variety of catalysts can be used, such as dibutyl tin dilaurate for isocyanate based reactions, tertiary amines such as triethylenediamine or phosphonium based catalysts for epoxy reaction and sulfonic acids, such as dodecylbenzene sulfonic acid for melamine reactions.

The coating compositions of the present invention are formulated into high solids coating systems dissolved in at least one solvent. The solvent is usually organic. Preferred solvents include aromatic hydrocarbons such as petroleum naphtha or xylenes; ketones such as methyl amyl ketone, methyl isobutyl ketone, methyl ethyl ketone or acetone; esters such as butyl acetate or hexyl acetate; and glycol ether esters such as propylene glycol monomethyl ether acetate.

The coating compositions of the present invention can also contain up to 30% of total binder of an acrylic polymer of weight average molecular weight greater than 3,000, or a conventional polyester such as SCDÖ - 1040 from Etna Product Inc. for improved appearance, sag resistance, flow and leveling and such. The acrylic polymer can be composed of typical monomers such as acrylates, methacrylates, styrene and the like and functional monomers such as hydroxy ethyl acrylate, glycidyl methacrylate, or gamma methacrylyl propyl trimethoxy silane and the like.

The coating compositions of the present invention can also contain up to 30% of total binder of a dispersed acrylic component which is a polymer particle dispersed in an organic media, which particle is stabilized by what is known as steric stabilization. Hereafter, the dispersed phase or particle, sheathed by a steric barrier, will be referred to as the "macromolecular polymer" or "core". The stabilizer forming the steric barrier, attached to this core, will be referred to as the "macromonomer chains" or "arms".

The dispersed polymer contains about 10 to 90%, preferably 50 to 80%, by weight, based on the weight of the dispersed polymer, of a high molecular

weight core having a weight average molecular weight of about 50,000 to 500,000. The preferred average particle size is 0.1 to 0.5 microns. The arms, attached to the core, make up about 10 to 90%, preferably 10 to 59%, by weight of the dispersed polymer, and have a weight average molecular weight of about 1,000 to 30,000, preferably 1,000 to 10,000.

The macromolecular core of the dispersed polymer is comprised of polymerized acrylic monomer(s) optionally copolymerized with ethylenically unsaturated monomer(s). Suitable monomers include styrene, alkyl acrylate or methacrylate, ethylenically unsaturated monocarboxylic acid, and/or silane-containing monomers. Such monomers as methyl methacrylate contribute to a high Tg (glass transition temperature) dispersed polymer, whereas such "softening" monomers as butyl acrylate or 2-ethylhexylacrylate contribute to a low Tg dispersed polymer. Other optional monomers are hydroxyalkyl acrylates or methacrylates or acrylonitrile. Optionally, the macromolecular core can be crosslinked through the use of diacrylates or dimethacrylates such as allyl methacrylate or post reaction of hydroxyl moieties with polyfunctional isocyanates.

The macromonomer arms attached to the core can contain polymerized monomers of alkyl methacrylate, alkyl acrylate, each having 1 to 12 carbon atoms in the alkyl group, as well as glycidyl acrylate or glycidyl methacrylate or ethylenically unsaturated monocarboxylic acid for anchoring and/or crosslinking. Typically useful hydroxy-containing monomers are hydroxy alkyl acrylates or methacrylates as described above.

The coating compositions of the present invention can also contain conventional additives such as pigments, stabilizers, rheology control agents, flow agents, toughening agents and fillers. Such additional additives will, of course, depend on the intended use of the coating composition. Fillers, pigments, and other additives that would adversely effect the clarity of the cured coating will not be included if the composition is intended as a clear coating.

The coating compositions are typically applied to a substrate by conventional techniques such as spraying, electrostatic spraying, roller coating, dipping or brushing. The present formulations are particularly useful as a clear coating for outdoor articles, such as automobile and other vehicle body parts. The substrate is generally prepared with a primer and or a color coat or other surface preparation prior to coating with the present compositions.

After application to a substrate, the present compositions can be cured by heating to a temperature of about 120°-150°C for a period of about 15 to 90 minutes.

The present invention is further illustrated by the following Procedures and Examples, in which parts and percentages are by weight unless otherwise indicated. VOC determinations are made by the procedure of ASTM method D3960.

5

Procedure 1

TETRA HYDROXYL FUNCTIONAL OLIGOMER

Preparation of Acid Oligomer

To a 12-liter flask fitted with an agitator, condenser, heating mantle,
10 nitrogen inlet, thermocouple and an addition port was added 2447.2 gms of propylene glycol monomethylether acetate, 792.4 gms of pentaerythritol and 1.36 gms of triethylamine. The reaction mixture was agitated and heated to 140°C under a nitrogen blanket at which time 3759 gms of methyl hexahydrophthalic anhydride was added over 6 hrs. The reaction mixture was then held at 140°C until no
15 anhydride bands were observed on an infrared spectroscopic trace.

Preparation of Diol

To a 5-liter flask fitted with an agitator, condenser, heating mantle, nitrogen inlet, thermocouple and an addition port was added 2798.4 gms of acid oligomer prepared above and 2.76 gms of triethylamine. The mixture was agitated
20 and heated to 60°C under nitrogen. Then, 696.9 gms of 1,2-epoxy butane was added over 120 mins, after which the temperature was raised to 105°C and held at that temperature until the acid number dropped to about 10 or less. Percent weight solids were 71.5, Gardner viscosity V, number average molecular weight 895 and weight average molecular weight 1022 as determined by GPC (polystyrene
25 standard).

Procedure 2

DI HYDROXYL FUNCTIONAL OLIGOMER

Preparation of Acid Oligomer

30 To a 12-liter flask fitted with an agitator, condenser, heating mantle, nitrogen inlet, thermocouple and an addition port was added 2434.5 gms of propylene glycol monomethylether acetate, 1222.5 gms of hexane diol and 1.37 gms of triethylamine. The reaction mixture was agitated and heated to 140°C under a nitrogen blanket at which time 3341.6 gms of methyl hexahydrophthalic anhydride
35 was added over 6 hrs. The reaction mixture was then held at 140°C until no anhydride bands were observed on an infrared spectroscopic trace.

Preparation of Oligomeric Diol

To a 5-liter flask fitted with an agitator, condenser, heating mantle, nitrogen inlet, thermocouple and an addition port was added 2020.4 gms of acid oligomer prepared above and 2.45 gms of triethylamine. The mixture was agitated and heated to 60°C under nitrogen. Then, 478.3 gms of 1,2-epoxy butane was added over 120 mins, after which the temperature was raised to 105°C and held at that temperature until the acid number dropped to about 10 or less. Percent weight solids were 69.5, Gardner viscosity A, number average molecular weight 679 and weight average molecular weight 770 as determined by GPC (polystyrene standard).

10

Procedure 3

HYDROXYL/SILANE OLIGOMER

The oligomer from Procedure 2 was further reacted by mixing

di hydroxyl functional oligomer	250
isocyanato propyl trimethoxy silane	60.9
1% dibutyl tin dilaurate in methylethyl ketone (MEK)	0.25

15

The above mixture was heated at 60°C for 3 days. The completion of the reaction was monitored by infra red spectroscopy. The reaction was complete when there was essentially no isocyanate absorption in the IR.

20

Procedure 4

ANHYDRIDE OLIGOMER

The anhydride oligomer was prepared from a tetra-functional half-acid ester. The following constituents were charged to a reaction vessel equipped with a heating mantle, reflux condenser, thermometer, nitrogen inlet, and stirrer:

25

<u>Portion I</u>	Parts by <u>Weight</u>
pentaerythritol	478.0
methyl hexahydrophthalic anhydride	2250.0
triethylamine	0.5
<u>Portion II</u>	
xylol (135°-145°C)	<u>2250.0</u>
Total	4978.5

30

Portion 1 was charged into the reaction vessel, heated to 180°C under a nitrogen blanket and held for 30 minutes. After the hold period, the reaction mixture was cooled and Portion 2 added.

35

The solution prepared above was used to make a linear pendant anhydride. The solution was charged into a 5L flask equipped with a stirrer and a gas inlet tube. The gas inlet tube was attached to a ketene generator similar to the one described by Williams et al in the Journal of Organic Chemistry 5, 122, 1940.

- 5 Ketene was bubbled through the solution until all of the acid groups were converted to anhydride groups. Solvent was then removed under vacuum to give a linear pendant anhydride with the following characteristics:

percent weight solids: 78.0

anhydride eq. wt.: 329 ± 4 (on solution basis)

10 acid eq. wt.: 6176 ± 1323 (on solution basis)

weight average mol wt. = 1100.

Example 1

ISOCYANATE CLEAR

15		Parts by
	<u>Part I</u>	<u>Weight</u>
	tetra hydroxyl functional oligomer	217.71
	(Procedure 1)	
	di hydroxyl functional oligomer	149.24
20	(Procedure 2)	
	propylene glycol mono methyl ether acetate	26.14
	(PM acetate)	
	Tinuvin [®] 384 (UV screener from Ciba Geigy)	8.94
	Tinuvin [®] 292 (hindered amine light stabilizer	6.72
25	from Ciba Geigy)	
	10% BYK - 301 [®] (flpw additive from BYK Chemie)	1.78
	in PM acetate	
	10% di butyl tin dilaurate in methyl ethyl ketone	1.12
	butyl acetate	52.27
30	<u>Part II</u>	
	Tolonate [®] HDT (isocyanurate trimer of	192.23
	hexamethylene diisocyanate from	
	Rhone-Poulenc)	

- 35 This coating was sprayed over a black waterborne basecoat which had already received a warm air flash of 5 min at 82°C (180°F). The coating was cured for 30 min at 141°C (285°F). The coating exhibited excellent appearance, hardness and mar resistance. This coating exhibited higher hardness and significantly better mar resistance than a standard coating made at a similar final film Tg using a routine hydroxyl functional acrylic polymer (6,000 weight average

molecular weight polymer with 32% hydroxy ethyl acrylate). The acrylic resin was substituted for the oligomer on an equivalent basis.

	<u>PROPERTY</u>	<u>OLIGOMERIC 2K CLEAR</u>	<u>POLYMERIC 2K CLEAR</u>
5	Glass Transition Temperature ¹	42.7°C	48.1°C
	Hardness ²	141 N/mm ²	130 N/mm ²
	Wet mar ³	80%	50.6%
	Dry mar ⁴	94.2%	65.5%
10	1 - as measured by differential scanning calorimetry		
	2 - as measured using a Fischerscope [®] hardness tester (the measurement is in Newtons per square millimeter)		
	3 - the surface of a panel is marred using a 3% slurry of aluminum oxide in water and a felt pad, the marring is accomplished using a Daiei [®] Rub Tester.		
15	The test uses 10 cycles with a weight of 500 grams. The rating shown is the percent of the surface which is not marred as measured by image analysis.		
	4 - the surface of a panel is marred using Bon Ami [®] Cleanser and a felt pad, the marring is accomplished using a Daiei [®] Rub Tester. The test uses 15 cycles with a weight of 700 grams. The rating shown is the percent of the surface		
20	which is not marred as measured by image analysis.		

Example 2

ANHYDRIDE/EPOXY CLEAR

	<u>Part I</u>	Parts by <u>Weight</u>
25	anhydride oligomer (Procedure 4)	763.08
	Tinuvin [®] 384 (UV screener from Ciba Geigy)	19.08
	Tinuvin [®] 292 (hindered amine light stabilier from Ciba Geigy)	13.74
30	5% BYK-301 [®] (flow additive from BYK Chemie) in PM acetate	56.4
	25% tetra butyl phosphonium chloride in PM acetate	19.84
	butyl acetate	97.0
35	<u>Part II</u>	
	diglycidyl ester of cyclohexane dicarboxylic acid	358.65

This coating was sprayed over a black waterborne basecoat which had already received a warm air flash of 5 min at 82°C. The coating was cured for

30 min at 141°C. This coating exhibited excellent appearance, hardness, cure and durability. This coating exhibited significantly better durability than a similar coating based on a standard acrylic anhydride polymer (a 6,000 weight average molecular weight polymer containing 27% itaconic anhydride). The acrylic was substituted for the oligomer on an equivalent basis. On accelerated QUV testing (using an FS-40 bulb), the polymeric anhydride based coating cracked after 4,000 - 6,000 hours of exposure; the oligomeric based coating showed no cracking and had excellent gloss at over 10,000 hours of exposure.

10

Example 3
MELAMINE CLEAR

	<u>Part I</u>	<u>Parts by Weight</u>
15	tetra hydroxyl functional oligomer (Procedure 1)	16.1
	di hydroxyl functional oligomer (Procedure 2)	16.6
	CymelÖ 1168 (melamine from Cytec Ind.)	16.1
20	20% BYK-301Ö (flow additive from BYK Chemie) in PM acetate	0.4
	catalyst solution*	0.8
	*catalyst solution	
	CycatÖ 600 (sulfonic acid from American Cyanamid)	48.0
	AMP-95Ö (amine from Angus Chemical)	10.8
25	methanol	41.2

This coating was applied over a black waterborne basecoat which had already received a warm air flash of 5 min at 82°C. The coating was cured for 30 min at 141°C. This coating exhibited good appearance, hardness, and mar resistance.

30

Example 4
SILANE (a) /HYDROXYL (b) /ISOCYANATE (c)

	<u>Part I</u>	<u>Parts by Weight</u>
35	tetra hydroxyl functional oligomer (Procedure 1)	243.5
	hydroxyl/silane oligomer (Procedure 3)	175.9

	TinuvinÖ 384 (UV screener from Ciba Geigy)	9.47
	TinuvinÖ 292 (hindered amine light stabilier from Ciba Geigy)	6.97
5	10% BYK-301Ö (flow additive from BYK Chemie) in PM acetate	3.29
	10% di butyl tin dilaurate in butyl acetate	1.04
	butyl acetate	26.3
	PM acetate	26.3

Part II

10	TolonateÖ HDT (isocyanurate trimer of hexamethylene diisocyanate from Rhône-Poulenc)	157.2
----	--	-------

This coating was sprayed over a black waterborne basecoat which
had already received a warm air flash of 5 min at 82°C. The coating exhibited
15 excellent appearance, hardness and mar resistance.

Example 5A.) Nonaqueous Dispersion

To a 5-liter flask fitted with a agitator, thermometer, condenser and
20 addition funnels was added the following ingredients. The mixture was agitated
under nitrogen and temperature raised to reflux (100° to 104°C). Ingredients are
given in parts by weight (to the nearest whole number, for most). The dispersed
polymer is 63.5% weight solids in toluene having a weight average molecular weight
of 8100. The composition was as follows:

25	STY/BA/BMA/HEA/MAA/GMA (14.7/43.6/27.5/10.1/2.3/1.7)	
	dispersed polymer	206
	isopropanol	12
	spirits	94
	heptane	53
30	butanol	3

Added as a shot at reflux was t-butyl peroctoate (0.5 parts) and
mineral spirits (5 parts). Then, the following ingredients were added over a 210
minute period at reflux:

35	styrene	52
	hydroxy ethylacrylate	86
	methyl methacrylate	126
	glycidyl methacrylate	5
	methacrylic acid	14

methyl acrylate	62
dispersed polymer	103

These ingredients were added next and the reaction held for 45

5 minutes:

butanol	12
heptane	17
t-butyl peroctoate	5
10 mineral spirits	31

Butanol (16 parts) and t-butyl peroctoate (1.7 parts) were then added over a 30 minute period and the reaction was held for 60 minutes. Finally, the reactor was stripped of 76 parts of solvent. The particle size was 298 nm as measured by quasielastic light scattering and had a room temperature viscosity of 2000 centipoise at 5 rpm on a Brookfield viscometer and a weight solids of 63.5 percent.

B.) Acrylosilane Resin

20 The resin was made by this procedure: charge 400 g of 2 ethyl hexanol and 400 g of N-pentyl propionate to a 5 liter flask. Heat to reflux. Premix and add 896 g of styrene, 672 g of gamma methacryl propyl trimethoxy silane, 336 g of 2-ethyl hexyl methacrylate, 336 g of hydroxypropyl methacrylate, 170.2 g of 2.2(2 methyl butane nitrile), 40 g of 2 ethyl hexanol, and 40 g of N-pentyl propionate to the refluxing material over a period of six hours. After the addition, hold the temperature for 30 minutes. Then, add a premixed blend of 40 g of 2 ethyl hexanol, 40 g of N-pentyl propionate and 9 g of 2.2(2 methyl butane nitrile) over a 30 minute period. Hold the temperature for 30 minutes after addition, then cool and empty.

30

Gardner Holt Viscosity	Weight Solids	Weight Ave. M.W.
X +1/2	73.3%	5686

C.) Cyclosilane Oligomer (i)

35 Place some cyclohexanedimethanol in the oven to melt. Once melted, take 294.7 g of cyclohexanedimethanol along with 0.11 g Fascat[®] 420 (tin catalyst from Elf Atochem) and place in a flask at about 35°C. Then, add 839 g of

isocyanate propyl trimethoxysilane over 75 minutes. Then hold for two hours. Cool and empty.

	Gardner Holt Viscosity	Weight Solids	Weight Ave. M.W.
5	V	90%	1550

D.) Silanated Star Polyester (i)

- Step I: Add the following ingredients to the reactor, heat to 120°C - 125°C. Allow batch to exotherm to 145°C. If exotherm does not happen heat to 145°C. Hold for 1 hour at 145°C before proceeding.

<u>Ingredient</u>	<u>Weight</u>
pentaerythritol	280.2
4-methyl hexahydrophthalic anhydride	1037.8
butyl acetate	161.1

- Step II: Feed the ingredients over 30 minutes at 145°C. Maintain the 145°C temperature.

Cardura E (monoepoxy from Shell Chemical)	1561.9
butyl acetate	182.3

- Step III: Add as a shot to reactor. Heat to 175°C. Record Acid Number vs. time profile, every 30 minutes after reaching 175°C, until it stabilizes.
- | | |
|----------------------|------|
| dibutyltin dilaurate | 2.9 |
| butyl acetate | 71.7 |

Step IV: Once acid number has stabilized, cool to below 100°C. Dilute with butyl acetate.

butyl acetate	302
Batch Total	3600

wt. solids = 80%

Acid Number < 2.

- In a reaction flask, place 3720 g of the star polyester made immediately above, 1524 g of isocyanate propyl trimethoxysilane and 0.1 g Fascat 420 catalyst. Stir for 90 minutes. Blanket the whole time with N₂.
- wt. solids = 86.3
Wt. Ave M.W. = 2200

E.) Clearcoat Composition Grams

Resimine 6550 (melamine from Monsanto)	14.43
---	-------

	Nonaqueous Dispersion (A)	26.77
	Acrylosilane Resin (B)	11.6
	Cyclosilane Oligomer (C)	22.22
	Silanated Star Polyester (D)	23.17
5	Catalyst Solution*	3.55
	Dibutyltin Dilaurate	0.2
	Resiflow SÖ (acrylic flow agent from Estron Chemical)	0.4
	Tinuvin 384	2.32
10	(UV Screener from CIBA Geigy)	
	Tinuvin 123	2.2
	(Hindered Amine light stabilizer from CIBA Geigy)	
	*Catalyst solution	
	CycatÖ 600 (sulfonic acid from American Cyanamid)	48.0
15	AMP-95Ö (amine from Angus Chemical)	10.8
	methanol	41.2

- This coating was applied over a black waterborne basecoat which had already received a warm air flash of 5 min at 82°C. The coating was cured for 30 min at 141°C. This coating exhibited good appearance, hardness, etch and mar resistance.
- 20

Claims:

1. A curable coating composition of a binder in an organic solvent, the composition having a volatile organic content not exceeding about 0.4 kilograms per liter, comprising:
 - 5 i) a binder selected from a linear or branched cycloaliphatic moiety-containing oligomer or blend of oligomers with a weight average molecular weight not exceeding about 3,000, a polydispersity not exceeding about 1.5 and functionality A or A plus B; and
 - 10 ii) an optional oligomeric crosslinker or blend of crosslinkers with a weight average molecular weight not exceeding about 3,000 and functionality C or C plus D;
 components i and ii reacting at cure to form a three-dimensional network having chains of substantially uniform, controllable molecular weight between crosslinks.
2. A composition according to Claim 1 wherein there are
 - 15 components i) and ii).
3. A composition according to Claim 1 wherein component i) contains functionality capable of crosslinking with itself, there being no component ii).
4. A composition according to Claim 1 wherein the oligomer of
 - 20 component i) comprises an oligomeric ester.
5. A composition according to Claim 1 wherein component ii) has a polydispersity not exceeding about 1.5.
6. A composition according to Claim 1 selected from the group consisting of: A is hydroxyl and C is isocyanate; A is anhydride or acid and C is epoxy; A is epoxy and C is isocyanate; A is hydroxyl and C is melamine; A is aldimine or ketimine, B is optionally hydroxyl, and C is isocyanate; A is epoxy, B is hydroxyl and C is isocyanate; A is silane, B is hydroxyl and C is melamine; A is acid, B is hydroxyl, C is epoxy and D is melamine; and A is silane, B is epoxy, C is acid and D is melamine.
 - 25
7. A composition according to Claim 1 additionally containing
 - 30 (i) up to 30 percent by weight of total binder of an acrylic polymer or polyester with weight average molecular weight greater than 3,000; or
 - (ii) up to 30 percent by weight of total binder of a noncyclic oligomer with a weight average molecular weight not exceeding about 3,000, a
 - 35 polydispersity not exceeding about 1.5 and functionality A or A plus B; or

(iii) up to 30 percent by weight of total binder of an acrylic component comprising a core of acrylic polymer and, grafted thereto, a plurality of substantially linear stabilizer components, this component containing at least about 2 percent of ethylenically unsaturated monomer with functionality capable of
5 reacting with (i), (ii), or both (i) and (ii), the core being substantially insoluble and the stabilizer components being soluble in the solvent medium.

8. A composition according to Claim 1 additionally containing up to 200 parts by weight, based on 100 parts of (i) and (ii), of pigment.

9. A method for coating a substrate comprising applying thereto a
10 composition according to Claim 1 and curing the composition.

10. A substrate coated with the composition of Claim 1.

INTERNATIONAL SEARCH REPORT

Intern: al Application No
PCT/US 97/08179

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C09D201/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 96 01864 A (E.I. DU PONT DE NEMOURS AND COMPANY) 25 January 1996 -----	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

26 September 1997

Date of mailing of the international search report

24.10.97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mazet, J-F

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/08179

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9601864 A	25-01-96	CA 2192948 A	25-01-96
		EP 0770103 A	02-05-97

Form PCT/ISA/210 (patent family sheet) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.